

Product	Temperature		Product	Temperature		Product	Temperature		Product	Temperature	
	23°	60°		23°	60°		23°	60°		23°	60°
Acetaldehyde	LR	NR	Castor oil (all conc.)	R	R	Hydrocyanic acid	R	R	Silver nitrate (sol.)	R	R
Acetic acid (10%)	R	R	Carbonic acid	R	R	Hydrogen	R	R	Sintetical detergents	R	R
Acetic acid (50%)	R	LR	Chlorine (100% dry gas)	LR	NR	Hydrogen sulphide acid	R	R	Soap solution (all conc.)	R	R
Acetic Anhydride	NR	NR	Chlorobenzene	NR	NR	Hypochlorous acid	R	R	Sodic Phosphate (tri)	R	R
Acetone	R	LR	Chloroform	LR	NR	Hydroquinone	R	R	Sodium acetate	R	R
Acetylsalicylic acid	R	R	Chlorosulphonic acid (100%)	NR	NR	Ink	R	R	Sodium benzoate (35%)	R	R
Air	R	R	Chlorowater (2%)	R	R	Iodine (sol. in KI)	LR	NR	Sodium bicarbonate	R	R
Alcohol from coconut oil	R	R	Cider	R	R	Lacquer paint	R	R	Sodium dichromate	R	R
Alum (all types)	R	R	Citric acid	R	R	Lactic acid	R	R	Sodium bisulphate	R	R
Aluminium chloride (all conc.)	R	R	Coffee	R	R	Lait	R	R	Sodium bisulphite	R	R
Amino acid	R	R	Concentrated of cola	R	R	Leach (10%)	R	R	Sodium borate	R	R
Amylic alcohol	R	R	Copper cyanide (sat.)	R	R	Lead acetate	R	R	Sodium bromide	R	R
Amyl acetate	NR	NR	Copper chloride (sat.)	R	R	Lead nitrate	R	R	Sodium carbonate	R	R
Amyl chloride	NR	NR	Copper fluoride (2%)	R	R	Liquid chlorine	NR	NR	Sodium cyanide	R	R
Ammonia (100% gas)	R	R	Copper nitrate (sat.)	R	R	Magnesium Carbonate	R	R	Sodium chlorate	R	R
Ammonium carbonate	R	R	Copper sulphide (sat.)	R	R	Magnesium chloride	R	R	Sodium chloride	R	R
Ammonium chloride (sat.solution)	R	R	Cotton oil	R	R	Magnesium hydroxide	R	R	Sodium ferrous/Cyanide	R	R
Ammonium fluoride (sat.solution)	R	R	Dextrin	R	R	Magnesium nitrate	R	R	Sodium fluoride	R	R
Ammonium hydrate (10%)	R	R	Dextrose	R	R	Magnesium sulphate	R	R	Sodium hydroxide	R	R
Ammonium hydrate (30%)	R	R	Dextrose (aqueous sat.sol)	R	R	Maize oil	R	R	Sodium hypochlorite	R	R
Ammonium nitrate (sat.solution)	R	R	Diazo salt	R	R	Mercury	R	R	Sodium nitrate	R	R
Ammonium persulphate	R	R	Dibutylphthalate	LR	LR	Methyl alcohol (100%)	R	R	Sodium sulphate	R	R
Ammonium sulphate	R	R	Dichloroethane	NR	NR	Methylene chloride (100%)	LR	NR	Sodium sulphite	R	R
Aniline	NR	NR	Dichlorobenzene (ortho e para)	NR	NR	Mineral oil	R	LR	Sodium sulphide	R	R
Aqua regia	NR	NR	Diesel *	R	R	n-heptane	LR	LR	Solution for brass plating	R	R
Aromatic hydrocarbon	NR	NR	Diethyl ketone	LR	LR	n-Octane	R	R	Solution for Cadmium plating	R	R
Arsenic acid (all conc.)	R	R	Diethylene glyco	R	R	Naphtha	LR	NR	Solution for Copper plating	R	R
Ascorbic acid (10%)	R	R	Diglycolic acid	R	R	Naphthalene	NR	NR	Solution for gold plating	R	R
Barium carbonate (sat.solution)	R	R	Dimethylamine	NR	NR	Nickel chloride	R	R	Solution for Lead plating	R	R
Barium chloride (sat.solution)	R	R	Domestic diesel *	R	R	Nickel nitrate	R	R	Solution for Nickel plating	R	R
Barium hydrator	R	R	Emulsion paint	R	R	Nickel sulphate	R	R	Solution for Silver plating	R	R
Barium sulphate (sat.solution)	R	R	Ethyl acetate	LR	NR	Nicotine (diluted)	R	R	Solution for Tin plating	R	R
Barium sulphide (sat.solution)	R	R	Ethyl benzene	NR	NR	Nitric acid (30%)	R	R	Solution for Zinc plating	R	R
Bathing agents	R	R	Ethyl chloride	NR	NR	Nitric acid (50%)	R	LR	Spirit	LR	NR
Beer	R	R	Ethylene glycol	R	R	Nitric acid (70%)	R	LR	Starch (sat.solution)	R	R
Benzene	NR	NR	Ethylic alcohol	R	R	Nitric acid (95%)	NR	NR	Stearic acid	R	R
Benzene hexachloride	R	R	Ethylic alcohol (35%)	R	R	Nitrobenzene	NR	NR	Sulphate aluminium (all conc.)	R	R
Benzoic acid (all conc.)	R	R	Ethylic ether	NR	NR	Olive oil	R	NR	Sulphurous acid)	R	R
Bismuth carbonate (sat.solution)	R	R	Exanol (tertiary)	R	R	Oxalic acid	R	R	Sulphuric acid (smoking)	NR	NR
Bisodic Phosphate	R	R	Ferrous chloride (ico)	R	R	Paint	R	R	Sulphuric acid (10%)	R	R
Bitumen	R	LR	Ferrous chloride (oso)	R	R	Paint solution	R	R	Sulphuric acid (50%)	R	R
Borax	R	R	Ferrous nitrate (ico)	R	R	Perchloroethylene	NR	NR	Sulphuric acid (70%)	R	LR
Boric acid (all conc.)	R	R	Ferrous sulphate (oso)	R	R	Petrol	NR	NR	Sulphuric acid (80%)	R	NR
Boron trifluoride	R	R	Fertilizers	R	R	Pickle	R	R	Sulphuric acid (96%)	LR	NR
Bromo (liquid)	NR	NR	Fluids for paint	R	R	Potassium bicarbonate	R	R	Sulphuric acid (98%)	LR	NR
Butane diol (100%)	R	R	Fluoboric acid	R	R	Potassium bromide	R	R	Tannic acid	R	R
Butane diol (10%)	R	R	Fluoride aluminium (all conc.)	R	R	Potassium carbonate	R	R	Tetrahydrofuran	LR	NR
Butane diol (50%)	R	R	Fluosilic acid	R	LR	Potassium chlorate	R	R	Tin chloride (ico)	R	R
Butyl acetate	NR	NR	Fluosilic acid (30%)	R	R	Potassium cyanide	R	R	Tin chloride (oso)	R	R
Butyl phenol	R	R	Formic acid (all conc.)	R	R	Potassium hydroxide (conc.)	R	R	Titanium tetrachloride	NR	NR
Butylic alcohol	R	R	Fosforic acid	R	LR	Potassium nitrate	R	R	Toluene	LR	NR
Butyric acid (all conc.)	NR	NR	Fosforic acid (30%)	R	R	Potassium perchlorate (10%)	R	R	Triethylene glycol	R	R
Cacao	R	R	Fructose	R	R	Potassium permanganate (20%)	R	R	Turpentine paint	LR	LR
Calcium bisulphite	R	R	Fruit pulp	R	R	Potassium persulphate	R	R	Verdigris	R	R
Calcium carbonate (sat.solution)	R	R	Furfural	NR	NR	Potassium sulphate (conc.)	R	R	Vinegar	R	R
Calcium chlorate (sat.solution)	R	R	Furfuryl alcohol	LR	NR	Potassium sulphite (conc.)	R	R	Xilene	NR	NR
Calcium chloride (sat.solution)	R	R	Gallic acid	R	R	Potassium sulphide (conc.)	R	R	Yeast	R	R
Calcium hydrate (all conc.)	R	R	Glucose	R	R	Propargyl alcohol	R	R	Water	R	R
Calcium nitrate (50%)	R	R	Glycerol	R	R	Propylene dichloride (100%)	NR	NR	Wine	R	R
Calcium oxide (sat.solution)	R	R	Glycol	R	R	Propylene glycol	R	R	Wiskey	R	R
Calcium sulphate	R	R	Glycolic acid	R	R	Propylic alcohol	R	R	Zinc bromide	R	R
Camphor oil	LR	NR	Hydrobromic acid (50%)	R	R	Pyridine	R	R	Zinc carbonate	R	R
Carbon dioxide	R	R	Hydrochloric acid (all conc.)	R	R	Resorcinol	R	R	Zinc chloride	R	R
Carbon disulphide	NR	NR	Hydrochloric acid (dry gas)	R	R	Salicylic acid	R	R	Zinc oxide	R	R
Carbon oxide (all conc.)	R	R	Hydrofluoric acid (40%)	R	R	Seawater	R	R	Zinc stearate	R	R
Carbon tetrachloride	LR	NR	Hydrofluoric acid (60%)	R	LR	Selenic acid	R	R	Zinc sulphate	R	R

Legend: R= Resistant LR= Limited Resistant NR= Not Resistant